Environment Conservation Journal 18 (1&2) 163-172, 2017 ISSN 0972-3099 (Print) 2278-5124 (Online) Abstracted and Indexed



# Effect of chlorine substitution on the removal of phenols by activated carbon

Suhas<sup>1</sup>⊠, Randhir Singh and Alka Harit

Received: 28.01.2017

Revised: 11.03.2017

Accepted: 10.04.2017

#### Abstract

A comparison of the removal of substituted phenols (2-chlorophenol, 4-chlorophenol and 2,4-dichlorophenol) with phenol using adsorption process on activated carbon has been investigated. The adsorption data was modeled using Langmuir and Freundlich equations and the Langmuir model was found to be the best fit. The removal of phenols by activated carbon followed a trend based on number of chlorine substitution with order: phenol < 2-chlorophenol < 4-chlorophenol < 2, 4-dichlorophenol. Substantial uptake of the phenols on activated carbon was observed and was found to be 0.83, 0.91, 0.93 and 1.51 mmol/g for phenol, 2-chlorophenol, 4-chlorophenol and 2,4-dichlorophenol, respectively. Pseudo-first order and pseudo-second order models were used to analyse the kinetic data and the process was found to follow pseudo-second order kinetic model.

Keywords: activated carbon, adsorption, chlorophenols, phenol, kinetics

### Introduction

Phenol and chlorophenols are considered as highly dispersed in aquatic environment while more toxic environmental contaminants that remain chlorinated chlorophenols spread less, even though persistent in atmosphere (Kakavandi et al. 2016). They act as starting materials or as intermediates in many chemical industries like resin, dyes, plastics, pharmaceutical, pulp and paper manufacturing industries (Priya and Madras 2006). Chlorophenols are used as herbicides, biocides, fungicides and are even available in water through drinking water chlorination (Quintana and Ramos 2008). Consumption of water containing phenol causes spasms, severe renal insufficiency and even death (Gundogdu et al. 2012). Furthermore, even at low level they act as irritants and may affect the central nervous and respiratory systems, besides this at a higher dose phenol can induce cancer too (Priya and Madras 2006). The degree of chlorination and chlorine atom position relative to the hydroxyl group affects the toxicity of chlorophenols (Czaplicka 2004). It is worthwhile mentioning that this degree of chlorination and the chlorine atom position may play an important role in their removal too. Further, it is interesting to note that chlorophenols with less number of chlorine are extremely hydrophilic, consequently they get easily

**Author's Address** 

Department of Chemistry, Gurukula Kangri Vishwavidyalaya, Haridwar, India E-mail:suhasnatyan@yahoo.com

to toxic substances compared to the other conventional methods of water purification has made this process much more popular (Mehta et al. Adsorption is a surface boundary 2015). phenomenon that involves the enrichment of the chemical species from the fluid phase on to the surface of liquid or solid (Worch 2012). The adsorption process either results from the Van der Waals interaction or it may involve chemical interaction (Dabrowski 2001). For adsorption process owing to well-developed porosity, large surface area and variable surface chemistry activated carbons are better choice as adsorbents for the removal of organic pollutants like phenols (Cotoruelo et al. 2007). The objectives of present work are to make a comparative study of the removal of substituted phenols (2-chlorophenol, 4-

they generally persist for longer time (Quintana and

Ramos 2008). The chlorophenols are weakly acidic

in nature and may permeate through human skin

and also get freely absorbed by gastrointestinal

tract, producing toxic effect (Domínguez-Vargas et

al. 2009). Among various methods available for the

removal of phenols adsorption process is a very effective technique and is generally used for the

elimination of these type of organic pollutants from

waste effluents. Higher efficiency and insensitivity

Copyright by ASEA

All rights of reproduction in any form reserved

163



chlorophenol and 2,4-dichlorophenol) and phenol using activated carbon developed from lignin and to investigate the effect of number and position of chlorine on the mechanism of adsorption. Furthermore, the aim is also to study the effect of different parameters such as contact time, initial phenol concentration and temperature. The parameters related to the adsorption isotherms and kinetics for the adsorption of phenols (phenol and chlorophenols) on activated carbon developed from lignin has also been evaluated.

#### **Material and Methods**

Phenol was purchased from Merck Pvt. Ltd. and 2chlorophenol, 4-chlorophenol, 2,4-dichlorophenol were purchased from Sigma Aldrich. The basic structural characteristic and selected properties of chlorophenols and phenols are listed in Table 1. Stock solutions  $(1 \times 10^{-2} \text{M})$  of phenols were prepared by dissolving the desired amount of phenol and chlorophenols in double distilled water. The stock solutions were diluted to get the desirable experimental concentration. The activated carbon utilized in the study was produced from a kraft lignin sample obtained from Lignotech Ibérica (Spain). For the production of the activated carbon the methodology as discussed elsewhere (Carrott et al. 2008) has been used. Almost 5g of lignin was placed in a ceramic boat and positioned in the central constant temperature zone of a conventional horizontal tubular furnace. Carbonisation was carried out by heating to 750°C at a rate of 8°Cmin<sup>-1</sup> under a constant N<sub>2</sub> flow of 85cm<sup>3</sup>min<sup>-1</sup> and maintaining for 30min. Physical activation in CO<sub>2</sub> was carried out by switching to a CO<sub>2</sub> flow of 85cm<sup>3</sup>min<sup>-1</sup> at same temperature (750°C) for 30 min and thereafter switching back to the N2 flow and allowing to cool to below 50°C before removing the AC from the furnace and storing in a sealed sample flask. The Brunauer-Emmett-Teller (BET) surface area of the activated carbon so developed was found to be 605  $m^2/g$  by N<sub>2</sub> adsorption.

#### **Batch adsorption studies**

Batch technique was used for the adsorption of phenols (phenol and chlorophenols) from aqueous solutions using the activated carbon synthesised from kraft lignin. For this 0.01g of the activated carbon was added to the stoppered glass tubes

containing 10 ml of solution with varying concentration. The samples were agitated in a thermostatted shaker at desired temperature until the equilibrium was achieved. The concentration of phenols and chlorophenols left unadsorbed in aqueous solutions were determined by using Agilent Cary 60 UV-Vis spectrophotometer at wavelength 274, 280, 285 and 270 nm for 2-chlorophenol, 4-chlorophenol, 2,4-dichlorophenol andphenol, respectively. All the experiments were carried out in duplicate and the mean value was used in all cases. The equilibrium adsorption capacity  $q_c$  (mmol/g)was calculated by using the following equation.

$$q_e = \frac{(C_o - C_e)V}{W} \tag{1}$$

where  $C_0$  and  $C_e$  are the initial and equilibrium concentrations in the solution (mol/L), respectively, V is the solution volume (L), and Wis the mass (g) of adsorbent used.

# Results and Discussion

# Effect of contact time

For the determination of appropriate contact time in order to remove phenol and chlorophenols (2chlorophenol, 4-chlorophenol and 2,4-dichloro phenol) the adsorption capacity of activated carbon was determined as a developed from lignin function of time and is shown in Fig.1. It can be observed from the Figure that during initial stage there is a rapid increase in adsorption followed by long period of much slower uptake until the equilibrium was achieved. This is due to the fact that during the initial stage of contact time a large number of free adsorption center are available for adsorption but after a interval of time residual free adsorption center were hard to be occupied due to the repulsion between the adsorbate molecule on the solid and bulk phases (Tan et al. 2009). The maximum amount of phenol and chlorophenols was removed in ~60 min and thereafter equilibrium was achieved in approximately 240 min. A small difference observed may be explained by the fact that the time of equilibration seems to be controlled by the molecular size of phenols. Large molecules may take comparatively longer time. However, the contact time was kept at 300 min for all molecules in further studies.



Effect of chlorine substitution on the removal of phenols



Fig.1 Effect of contact time on the uptake of a) phenol b) 2-chlorophenol c) 4-chlorophenol and d) 2,4-dichlorophenol on activated carbon developed from lignin

# Effect of initial phenol concentration

The effect of variation in the initial concentration on the adsorption of phenol and chlorophenols was studied. The amount adsorbed at two different concentrations is presented in Fig.1, which shows that the amount of phenols adsorbed increases on increasing the concentration. However, the percentage adsorption was found to decrease which may be due to the fact that on increasing the concentration adsorption centers of the adsorbent get saturated whereas, on the other hand the accessibility of centers available for adsorption are more at lower concentration for the binding of the adsorbate molecule.

# Adsorption isotherms

Adsorption isotherm describes the relationship between the concentration of the adsorbate on the solid phase and in the liquid phase (Jagadeesh Babu

et al. 2010). The adsorption isotherm obtained for chlorine substituted phenols (2-chlorophenol, 4chlorophenol and 2,4-dichlorophenol) along with phenol was studied as a function of concentration and the adsorption isotherms (at 25 and  $45^{\circ}$ C) obtained on activated carbon developed from lignin are shown in Fig. 2 and 3. The experimental adsorption values observed from the figure 2 at 25°C were found to be 0.83, 0.91, 0.93 and 1.51mmol/g for phenol, 2-chlorophenol, 4-chloro phenol and 2,4-dichlorophenol, respectively. These values obtained are compared with other activated carbons too (Table 1) in order to assess the removal efficiency of the present adsorbent and process. The results clearly show the process to be at par with other materials and justify the applicability of the process. Conventionally used models Langmuir as well as Freundlich were used to analyse the adsorption isotherms. Langmuir isotherm model



#### Suhas et al.

assumes monolayer adsorption on surface where  $q_e$  is the amount of the adsorbate adsorbed at containing finite number of energetically equivalent equilibrium concentration, qm is the theoretical identical sites and is represented by the following equation (Langmuir 1918).

$$\frac{1}{q_e} = \frac{1}{q_m} + \frac{1}{q_m b C_e}$$
(2)

0 2 0.0002 0.0004 0.0006 0.0008 0.001 0.0012 1.4 1.8 1.6 1.2 2 1.4 2 1 1 • 1 1.2 **1** 0.8 1 0.8 B/lomul/g B/lomu<sup>a</sup>b 0.8 0.6 phenol 0.4 0.4 ▲ 2-Chlorophenol 0.2 4-Chloropenol 0.2 2,4-dichlorophemnol 0 0 1, 0.0001 0.0002 0.0003 0.0004 0.0005 U C<sub>e</sub> , mol/L

Fig.2 Adsorption isotherms of phenol, 2-chlorophenol,

4-chlorophenol and 2,4-dichlorophenol on activated

carbon developed from lignin at 25 °C.



maximum adsorption capacity, b the Langmuir adsorption constant and Ce the equilibrium

concentration of the adsorbate.



Fig.3 Adsorption isotherms of phenol, 2-chlorophenol, 4-chlorophenol and 2,4-dichlorophenol on activated carbon developed from lignin at 45°C

S.no.	Adsorbate	Adsorbent	Surface area (m²/g)	Amount adsorbed (mg/g)	Reference
1	Phenol	Activated carbon from jackfruit peel	115.25	144.9	(Jain and Jayaram 2007)
		Activated carbon from kenaf	493	140.84	(Aber <i>et al.</i> 2009)
		Activated carbon(AC-P)	940	106.5	(Fierro <i>et al.</i> 2008)
		CAC 2 Activated carbon developed from lignin	620 605	73.91 78.47 (0.83 mmol/g)	This study
2	2-chloro phenol	Granular activated carbon	954	294	(Hossain and McLaughlan 2012)
		Activated carbon from jackfruit peel	115.25	243.9	(Jain and Jayaram 2007)
		Ricinus communis pericarp activated carbon		71.43	(Adane <i>et al.</i> 2015)
		Activated carbon developed from lignin	605	117.5 (0.91 mmol/g)	This study

	<b>Fable 1- Adsorption</b>	capacities of	different	adsorbents for	r the removal o	of phenols
--	----------------------------	---------------	-----------	----------------	-----------------	------------





3	4-Chloro Phenol	Activated carbon from jackfruit peel	115.25	277.7	(Jain and Jayaram 2007)
		Activated carbon (CWZ)	977	322	(Lorenc-Grabowska <i>et al.</i> 2010)
		Activated carbon CWZ N <sub>2</sub>	940	369	(Lorenc-Grabowska <i>et al.</i> 2010)
		Activated carbon CWZ NH3	914	263	(Lorenc-Grabowska <i>et al.</i> 2010)
		Activated carbon from waste coconut shells (csac)	935.24	72.7	(Radhika and Palanivelu 2006)
		Commercial activated carbon	838.45	134.09	(Radhika and Palanivelu 2006)
		Granular activated carbon	954	319	(Hossain and McLaughlan 2012)
		Carbon derived from refuse derived fuel (RDFN1)	898	416	(Wu <i>et al.</i> 2014)
		Activated carbon developed from lignin	605	119 (0.93mmol/g)	This study
4	2,4dichlorophe nol	Activated carbon from jackfruit peel	115.25	400	(Jain and Jayaram 2007)
		Granular activated carbon	954	467	(Hossain and McLaughlan 2012)
		Activated carbon from Prosopis africana seed hulls	1085.9	380.7	(Garba and Rahim 2016)
		Activated carbon fiber	702	372	(Wang et al. 2007)
		Activated carbon developed from lignin	605	245 (1.51mmol/g)	This study

Effect of chlorine substitution on the removal of phenols

In order to define the favorability of adsorption logarithmic form of the equation (Freundlich 1906) process a dimensionless constant separating factor or equilibrium parameter 'RL' is also calculated (Weber and Chakravorti 1974) using the following equation

$$R_{\rm L} = \frac{1}{1 + b C_0}$$
 (3)

where  $C_0$  is the initial concentration and b the Langmuir adsorption constant. The R<sub>L</sub> value indicate whether the adsorption is favourable  $(0 < R_L < 1)$ , linear  $(R_L=1)$ , irreversible  $(R_L=0)$ , or unfavourable ( $R_L > 1$ ). As the  $R_L$  values for all experiments were observed between 0 and 1, the adsorption can be said to be favorable in all cases. Besides Langmuir, Freundlich isotherm has also been widely used in order to study the adsorption process. Freundlich equation is an empirical equation that is very useful as it also accurately describes adsorption data. The well-known

is given by:

$$\log q_e = \log k_F + (1/n) \log C_e$$
 (4)

where  $q_e$  is the amount of the adsorbate adsorbed at the equilibrium concentration ,  $k_F$  and n are the constants that define the adsorption capacity and adsorption intensity, respectively. The plots of Langmuir  $(1/q_e \text{ versus } 1/C_e)$  and Freundlich (log  $q_e$ versuslog Ce)for the adsorption of phenol, 2chlorophenol, 4-chlorophenol and 2.4dichlorophenolon activated carbon from lignin at temperatures 25 and 45°C according to their linear form are shown in Figs. 4 and 5. The constant calculated from the linear form of the equations 3-4 are given in Table 2. It can be observed from Table that the experimental values at these temperature were found to be in well agreement with the theoretical value obtained from the Langmuir



found to be better for Langmuir model in

model. Moreover, the correlation coefficients are comparison to the Freundlich model thereby indicating the process to conform Langmuir model.



Fig.4 Langmuir adsorption isotherms of phenol, 2-chlorophenol, 4-chlorophenol and 2,4-dichlorophenol on on activated carbon developed from lignin a) 25 °C and b) 45 °C.



Fig.5 Freundlich adsorption isotherms of phenol, 2-chlorophenol, 4-chlorophenol and 2,4-dichlorophenol on activated carbon developed from lignin a) 25°C and b) 45°C

## Mechanism of adsorption and effect of chlorine deactivates the aromatic ring and makes it partially substitution on the removal

The adsorption capacity of phenol and chlorophenols from Fig. 2 was found to follow the order: 2,4-dichlorophenol > 4-chlorophenol > 2chlorophenol > phenol. This is due to the fact that on carbon surface and the aromatic ring. chlorine is an electron withdrawing group that Furthermore, the solubility (Table 3) of phenol and

positive in nature, as the number of chlorine atom increase this effect was found to be increase thereby resulting in the formation of donor-acceptor interaction between the oxygen containing groups



#### Effect of chlorine substitution on the removal of phenols

chlorophenols is found to be in the order: phenol > explains the higher adsorption capacity of 2-2-chlorophenol > 4-chlorophenol > 2,4- chlorophenol too in comparison of 4-chlorophenol dichlorophenol, which may also be the factor for though both contains one chloro group only. the adsorption to be in the reverse order, and this

Table 2: Langmuir and Freundlich isotherm constants and correlation coefficients for phenol, 2chlorophenol, 4-chlorophenol and 2,4-dichlorophenol adsorption onto activated carbon developed from lignin at different temperatures

Types of	Temperature	Langmuir			Freundlich		
Adsorbates	-	q <sub>m</sub>	b	$\mathbf{R}^2$	K <sub>f</sub>	n	$\mathbf{R}^2$
		(mmol/g)	(L/mmol)		(mmol/g)		
Phenol	25°C	0.90	$1.66 \times 10^{-4}$	0.996	107.15	1.73	0.961
	45°C	0.95	$1.87 \times 10^{-4}$	0.997	161.06	1.65	0.972
2-chlorophenol	25°C	0.93	$2.71 \times 10^{-4}$	0.999	80.87	1.90	0.959
	45°C	0.98	3.12×10 <sup>-4</sup>	0.988	65.71	2.02	0928
4-chlorophenol	25°C	0.96	$2.84 \times 10^{-4}$	0.966	109.39	1.83	0.956
	45°C	0.99	3.33×10 <sup>-4</sup>	0.991	153.85	1.76	0.968
2,4-dichlorophenol	25°C	1.45	$4.76 \times 10^{-4}$	0.998	10.96	3.85	0.878
	45°C	1.58	5.97×10 <sup>-4</sup>	0.997	13.04	3.79	0.873

Table 3- Structural characteristic and selected properties of phenol and chlorophenols

Phenols	Molecular weight	Structure	λmax (nm)	Solubility <sup>a</sup> (g/L of water)	pKa <sup>a</sup>
Phenol	94.11	OH	270	93	9.89
2-chlorophenol	128.56	OH	274	28	8.52
4-chlorophenol	128.56	OH G	280	27	9.37
2,4-dichlorophenol	163	CI CI	285	4.5	7.90

<sup>a</sup> (Dąbrowski et al. 2005)

This behaviour is usual and expected since molecules if have less solubility i.e., lesser affinity for water,tend to get adsorb more (Moreno-Castilla *et al.* 1995).

#### Effect of temperature and free energy change

A series of experiments have been conducted at higher temperature  $(45^{\circ}C)$  too keeping the rest parameters constant in order to study the effect of

temperature on adsorption and the results are shown in Fig. 3. The experimental adsorption values observed from the figure 3 were found to be 0.91, 1.00, 1.02 and 1.65 mmol/g for phenol, 2chlorophenol, 4-chlorophenol and 2,4dichlorophenol, respectively. It can be seen from the Figures 2 and 3 that amount adsorbed increases on increasing the temperature indicating the process to be endothermic in nature. The reason for this

169 Environment Conservation Journal



change can be explained on the basis of hydrogen bonding (Jain *et al.* 2004). Phenol molecules forms hydrogen bonds with water and thereby makes them appreciable soluble in water. However, when temperature is increased these bonds broke which in turn makes phenols less soluble and therefore, they exhibit higher tendency to go to the activated carbon surface and get adsorbed rather than remaining in the solution. This results in more adsorption at higher temperatures. Gibbs free energy change (equation 5) was also calculated at different temperatures using Langmuir constant and the value were found to be in the range of -24.1 to -29.1 kJ/mol.

$$\Delta G^{\circ} = -RTln(b) \tag{5}$$

The negative value of  $\Delta G^{\circ}$  obtained at different temperatures suggests that the process is spontaneous and thermodynamically favorable.

## Adsorption kinetics

Kinetic study for the adsorption of phenol and substituted phenols (2-chlorophenol, 4chlorophenol and 2,4-dichlorophenol) has been carried out up to 300 min. The pseudo-first order and pseudo-second order models were used for the kinetic studies. The pseudo-first order (Lagergren 1898) has been one of the widely used rate equations in the liquid adsorption and is given by:

$$\log (q_e - q_t) = \log q_e - \frac{k_1}{2.303} t$$
 (6)

where  $q_e$  and  $q_t$  are amount adsorbed at equilibrium and at time t respectively and  $k_1$  the pseudo-first order rate constant. Kinetic constants were obtained by plotting log ( $q_e - q_t$ ) versus time t in Fig. 6 and the values for kinetic parameters are shown in Table 4.

Table 4- Kinetic parameters for the adsorption of phenol, 2-chlorophenol, 4-chlorophenol and 2,4-dichlorophenol on activated carbon developed from lignin.

Types of	C <sub>0</sub> (mol/L)	q <sub>e</sub> (exp) (mmol/g)	Pseudo-first order			Pseudo-second order		
ausorbates			q <sub>e</sub> (cal)	<b>K</b> <sub>1</sub>	$\mathbf{R}^2$	q <sub>e</sub> (cal)	$\mathbf{K}_2$	$\mathbf{R}^2$
			(mmol/g)	( <b>1/min</b> )		(mmol/g	g) (g/mmol min)	
Phenol	$7.0 \times 10^{-4}$	0.525	0.323	1.18×10 <sup>-3</sup>	0.896	0.573	7.25×10 <sup>-2</sup>	0.998
2-chloro phenol	7.0×10 <sup>-4</sup>	0.563	0.384	7.83×10 <sup>-3</sup>	0.906	0.603	6.86×10 <sup>-2</sup>	0.999
4-chloro phenol	7.0×10 <sup>-4</sup>	0.569	0.315	9.21×10 <sup>-3</sup>	0.891	0.608	7.82×10 <sup>-2</sup>	0.999
2,4-dichloro phenol	$1.5 \times 10^{-4}$	1.22	0.387	1.2×10 <sup>-2</sup>	0.838	1.2586	$1.051 \times 10^{-1}$	0.999

Besides pseudo-first order rate equation, pseudosecond order equation (Ho and McKay 1998) was also applied to study the kinetics of process. The equation used is given as:

$$\frac{\mathrm{t}}{\mathrm{q}_{\mathrm{t}}} = \frac{1}{\mathrm{K}_{2}\mathrm{q}_{\mathrm{e}}^{2}} + \frac{\mathrm{t}}{\mathrm{q}_{\mathrm{e}}} \tag{7}$$

where  $q_e$  and  $q_t$  are the amount adsorbed at equilibrium and time t, respectively,  $k_2$  is the pseudo-second order rate constant and  $K_2q_e^2 = h$ the initial adsorption rate. A plot made between the  $t/q_t$  vs t is presented in Fig.7 and the values of  $k_2$ and  $q_e$  are determined from it. The experimental

data and parameters of both the models are given in the Table 4. The correlation coefficients ( $\mathbb{R}^2$ ) values obtained (Table 4) for the pseudo–second order were found to be high compared to the pseudo-first order. Further, the experimental  $q_e$  value was found to be in well agreement with the calculated value obtained from the pseudo-second order model. Therefore, it can be concluded that pseudo-second order kinetic model fitted well for adsorption of substituted phenols (2-chlorophenol, 4-chlorophenol and 2,4-dichlorophenol) as well as phenol on activated carbon developed from lignin.



## Conclusion

phenols (phenol as well as chlorophenols) can be



Fig.6 Pseudo-first order kinetics for adsorption of phenol, 2-chlorophenol, 4-chlorophenol and 2,4-dichlorophenol on activated carbon developed from lignin

an important role in the removal of phenols by activated carbon following an order as phenol<2chlorophenol<4-chlorophenol<2,4-dichlorophenol. Significant adsorption of the phenols on activated carbon was observed and was found to be 0.83, 0.91, 0.93 and 1.51 mmol/g for phenol, 2chlorophenol, 4-chlorophenol and 2,4dichlorophenol, respectively. The process was found to fit Langmuir model and followed pseudo-second order kinetics.

#### Acknowledgment

Alka Harit is thankful to the UGC for the financial support [Grant No. F-14-2(SC)/2010(SA-III)] and Suhas is grateful to Prof. P. J. M. Carrott, University of Evora, Portugal for providing laboratory facilities. The authors thank Dr. V. Fierro for providing the lignin sample.

#### References

Aber, S., Khataee, A. and Sheydaei, M. 2009. Optimization of activated carbon fiber preparation from Kenaf using K2HPO4 as chemical activator for adsorption of phenolic compounds. Bioresource Technology, 100(24); 6586-6591.

The current study shows that the removal of carried out efficiently by activated carbon using adsorption process. The chlorine substitution play



Fig.7 Pseudo-second order kinetics for adsorption of phenol, 2-chlorophenol, 4-chlorophenol and 2,4-dichlorophenol on activated carbon developed from lignin

- Adane, B., Siraj, K. and Meka, N. 2015. Kinetic, equilibrium and thermodynamic study of 2-chlorophenol adsorption onto Ricinus communis pericarp activated carbon from aqueous solutions. Green Chemistry Letters and Reviews, 8(3-4); 1-12.
- Carrott, P.J.M., Suhas, Carrott, M.M.L.R., Guerrero, C.I. and Delgado, L.A. 2008. Reactivity and porosity development during pyrolysis and physical activation in CO2 or steam of kraft and hydrolytic lignins. Journal of Analytical and Applied Pyrolysis, 82(2); 264-271.
- Cotoruelo, L.M., Marqués, M.D., Rodríguez-Mirasol, J., Cordero, T. and Rodríguez, J.J. 2007. Adsorption of Aromatic Compounds on Activated Carbons from Lignin: Equilibrium and Thermodynamic Study. Industrial & Engineering Chemistry Research, 46(14); 4982-4990.
- Czaplicka, M. 2004. Sources and transformations of chlorophenols in the natural environment. Science of The Total Environment, 322(1-3); 21-39.
- Dąbrowski, A. 2001. Adsorption from theory to practice. Advances in Colloid and Interface Science, 93(1-3); 135-224.
- Dąbrowski, A., Podkościelny, P., Hubicki, Z. and Barczak, M. 2005. Adsorption of phenolic compounds by activated carbon-a critical review. Chemosphere, 58(8); 1049-1070



- Domínguez-Vargas, J.R., Navarro-Rodríguez, J.A., de Heredia, J.B. and Cuerda-Correa, E.M. 2009. Removal of chlorophenols in aqueous solution by carbon black lowcost adsorbents. Equilibrium study and influence of operation conditions. *Journal of Hazardous Materials*, 169(1–3); 302-308.
- Fierro, V., Torné-Fernández, V., Montané, D. and Celzard, A. 2008. Adsorption of phenol onto activated carbons having different textural and surface properties. *Microporous and Mesoporous Materials*, 111(1–3); 276-284.
- Freundlich, H.M.F. 1906. Over the adsorption in solution. Journal of Physical Chemistry, 57; 385–470.
- Garba, Z.N. and Rahim, A.A. 2016. Evaluation of optimal activated carbon from an agricultural waste for the removal of para-chlorophenol and 2,4-dichlorophenol. *Process Safety and Environmental Protection*, 102; 54-63.
- Gundogdu, A., Duran, C., Senturk, H.B., Soylak, M., Ozdes, D., Serencam, H. and Imamoglu, M. 2012. Adsorption of Phenol from Aqueous Solution on a Low-Cost Activated Carbon Produced from Tea Industry Waste: Equilibrium, Kinetic, and Thermodynamic Study. *Journal of Chemical & Engineering Data*, 57(10); 2733-2743.
- Ho, Y.S. and McKay, G. 1998. Sorption of dye from aqueous solution by peat. *Chemical Engineering Journal*, 70(2); 115-124.
- Hossain, G.S.M. and McLaughlan, R.G. 2012. Sorption of chlorophenols from aqueous solution by granular activated carbon, filter coal, pine and hardwood. *Environmental Technology*, 33(16); 1839-1846.
- Jagadeesh Babu, P.E., Kumar, V. and Visvanathan, R. 2010. Equilibrium and kinetic study for the removal of malachite green using activated carbon prepared from Borassus flabellofer male flower. *Asia-Pacific Journal of Chemical Engineering*, 5(3); 465-472.
- Jain, A.K., Gupta, V.K., Jain, S. and Suhas 2004. Removal of Chlorophenols Using Industrial Wastes. *Environmental Science & Technology*, 38(4); 1195-1200.
- Jain, S. and Jayaram, R.V. 2007. Adsorption of Phenol and Substituted Chlorophenols from Aqueous Solution by Activated Carbon Prepared from Jackfruit (artocarpus heterophyllus) Peel-Kinetics and Equilibrium Studies. *Separation Science and Technology*, 42(9); 2019-2032.
- Kakavandi, B., Jahangiri-rad, M., Rafiee, M., Esfahani, A.R. and Babaei, A.A. 2016. Development of response surface methodology for optimization of phenol and pchlorophenol adsorption on magnetic recoverable carbon. *Microporous and Mesoporous Materials*, 231; 192-206.
- Lagergren, S. 1898. About the theory of so-called adsorption of soluble substances. *Kungliga svenska vetenskapsakademiens handlingar* 24; 1-39.

- Langmuir, I. 1918. The adsorption of gases on plane surfaces of glass, mica and platinum. *Journal of the American Chemical Society*, 40(9); 1361-1403.
- Lorenc-Grabowska, E., Gryglewicz, G. and Machnikowski, J. 2010. p-Chlorophenol adsorption on activated carbons with basic surface properties. *Applied Surface Science*, 256(14); 4480-4487.
- Mehta, D., Mazumdar, S. and Singh, S.K. 2015. Magnetic adsorbents for the treatment of water/wastewater—A review. *Journal of Water Process Engineering*, 7; 244-265.
- Moreno-Castilla, C., Rivera-Utrilla, J., López-Ramón, M.V. and carrasco-Marín, F. 1995. Adsorption of some substituted phenols on activated carbons from a bituminous coal. *Carbon*, 33(6); 845-851.
- Priya, M.H. and Madras, G. 2006. Kinetics of Photocatalytic Degradation of Chlorophenol, Nitrophenol, and Their Mixtures. *Industrial & Engineering Chemistry Research*, 45(2); 482-486.
- Quintana, M.C. and Ramos, L. 2008. Sample preparation for the determination of chlorophenols. *TrAC Trends in Analytical Chemistry*, 27(5); 418-436.
- Radhika, M. and Palanivelu, K. 2006. Adsorptive removal of chlorophenols from aqueous solution by low cost adsorbent—Kinetics and isotherm analysis. *Journal of Hazardous Materials*, 138(1); 116-124.
- Tan, I.A.W., Ahmad, A.L. and Hameed, B.H. 2009. Adsorption isotherms, kinetics, thermodynamics and desorption studies of 2,4,6-trichlorophenol on oil palm empty fruit bunchbased activated carbon. *Journal of Hazardous Materials*, 164(2–3); 473-482.
- Wang, J.-P., Feng, H.-M. and Yu, H.-Q. 2007. Analysis of adsorption characteristics of 2,4-dichlorophenol from aqueous solutions by activated carbon fiber. *Journal of Hazardous Materials*, 144(1–2); 200-207.
- Weber, T.W. and Chakravorti, R.K. 1974. Pore and solid diffusion models for fixed-bed adsorbers. *AIChE Journal*, 20(2); 228-238.
- Worch, E. 2012. Adsorption Technology in Water Treatment: Fundamentals, Processes, and Modeling, De Gruyter.
- Wu, F.-C., Wu, P.-H., Tseng, R.-L. and Juang, R.-S. 2014. Use of refuse-derived fuel waste for the adsorption of 4chlorophenol and dyes from aqueous solution: Equilibrium and kinetics. *Journal of the Taiwan Institute of Chemical Engineers*, 45(5); 2628-2639.



